

---

## Printed by EAST

---

UserID: mchristian  
Computer: TRN03097  
Date: 7/21/2008  
Time: 7:59:28 AM

## Document Listing

Document	Image pages	Text pages	HTML pages	Error Pages
JP 04094727 A	0	0	2	0
Total	0	0	2	0

PAT-NO: JP404094727A  
DOCUMENT- JP 04094727 A  
IDENTIFIER:  
TITLE: PRODUCTION OF AROMATIC POLYSULFONE SEMIPERMEABLE  
MEMBRANE EXCELLENT IN WATER PERMEABILITY

PUBN-DATE: March 26, 1992

INVENTOR-INFORMATION:

NAME	COUNTRY
YAMAMOTO, TAKAYUKI	
ONMURA, MASAMI	

ASSIGNEE-INFORMATION:

NAME	COUNTRY
NITTO DENKO CORP	N/A

APPL-NO: JP02212211

APPL-DATE: August 10, 1990

INT-CL (IPC): B01D071/68 , B01D071/40

US-CL-CURRENT: 210/500.41

ABSTRACT:

**PURPOSE:** To produce a semipermeable membrane with suppressed elution of hydrophilic resin under simple and mild conditions by dipping a semipermeable membrane comprising aromatic polysulfone containing hydrophilic resin in a polycarboxylic acid of specified compsn. and then treating the membrane by heating.

**CONSTITUTION:** A semipermeable membrane is produced from a membrane- producing solution containing hydrophilic resin such as polyvinylpyrrolidone, etc., and aromatic polysulfone. Then this semipermeable membrane is dipped in a polycarboxylic acid aq. soln. containing  $\alpha,\beta$ -unsatd. carboxylic acid such as polyacrylic acid, polyitaconic acid, etc., as the main monomer component, and then treated by heating to make the hydrophilic resin water-insoluble. The obtd. polysulfone semipermeable membrane has high water permeability without elution of hydrophilic resin and can be used for water treatment for a long time.

COPYRIGHT: (C)1992,JPO&Japio

